



Transport Pads

PVC Transport Pad

(Also available in **Red B0055.RED**)

General Description

Commonly used in the glazing industry as these are low tack and can be removed cleanly from materials.

The pads are constructed from a quick recovery PVC foam, a low tack solvent acrylic peelable adhesive and a 90gsm silicone release liner.

Standard Variants

B0055

Blue 21mm x 18mm x 4.3mm thick

Test Data

PROPERTIES	TEST METHOD	TYPICAL VALUE	UNIT
PVC Foam			
Density	ASTM 1667	275	kg/m ³
Tensile Strength	DIN 53571	≥ 450	kpa
Elongation at Break	DIN 53571	≥ 125	%
Tear Strength	DIN 53515	≥ 1.8	N/mm
Compression Set (50% / 23°C / 72h)	DIN 53572	≤ 15	%
Compression Deflection	ASTM 1667	0s. 40-85 60s. 15-50	Kpa
Shore Hardness	-	00	40 - 60
Water Absorption	-	≤ 15	%
Compression Water Seal	U Test	≥ 15	%
Flammability	FMVSS302	≤ 100 (> 2mm)	mm/min
Temperature Range	-	-30 / +60	°C
Adhesive			
Adhesive Type	Peelable Acrylic Pressure Sensitive	7 - 10 gsm	
Release Liner	Glassine paper with differential release	90 gsm	
Adhesion	180° peel from steel after 20 mins	0.2N / 25mm	

There is a +/- 10% manufacturing tolerance on all weights and measures

This data is to be used as information only and does not contain any guarantee as our products may be used for different purposes. Purchasers should conduct their own tests to determine the suitability of this material for their purposes.